

Regression Analysis of the Effects of Yarn Counts, Stitch Lengths on Depth of Stripes of Different Single Jersey Fabrics



Fahad Halim^{1*}, Iftay Khairul Alam² and Tahmina Akhter²

¹Department of Textile Engineering, World University of Bangladesh, India

²Department of Textile Engineering, European University of Bangladesh, India

Submission: July 24, 2019 ; Published: September 09, 2019

*Corresponding author: Fahad Halim, Department of Textile Engineering, World University of Bangladesh, India

Abstract

Fabric can be made attractive by means of ornamentation and designing. Stripe is one means by which attractive fabric can be produced which added extra values of that product. This research was to investigate the effects of yarn counts, Knit structures and Stitch Lengths on the depth of stripes. All the samples were made with 100% cotton dyed yarns. The work was done in three sections. In the first section, using a stitch length 2.8mm, three Single Jersey Plain structures were produced using different yarn counts which were 30 Ne, 28 Ne, and 26 Ne. In the second section, Single Jersey Plain, Single Lacoste, Polo Pique, and Double Lacoste structures were produced with 26 Ne yarn at stitch length 2.8mm. In the final section, four Single Jersey Plain structures were produced by varying stitch length 2.70 mm, 2.80 mm, 2.90 mm and 3.0 mm using the same yarn count which was 30 Ne. After conditioning, Depth of stripes (DOS) were measured, data were presented in tables and graphical representations were shown. It was found that little changes in DOS were observed with decreasing of yarn count in dry relaxed state but remarkable changes in DOS were observed after washing and wet relaxation. DOS for 30 Ne, 28 Ne, and 26 Ne were found 13.25 mm, 13.5 mm and 14.2 mm respectively. In the second section, the highest depth of stripe was found in Single Jersey Plain structure and lowest in Double Lacoste structure. Depths of stripes of other structures lie in between them. Effects of stitch lengths were also studied here. Effects of four different stitch lengths were shown in Single Jersey Plain structures. Depth of stripes in a dry relaxed state for 2.70 mm, 2.80 mm, 2.90 mm and 3.00 mm were found 11.1 mm, 13.35 mm, 13.85 mm and 14.30 mm respectively. Depths of stripes in wet relaxed state were reduced in all samples due to shrinkage.

Keywords: Regression analysis; yarn counts; Stitch lengths; Stripes; Single Jersey Fabrics; Knit structures; knitting; warp knits; knit loops; tuck loops; woven fabrics; miss loops; wrap reel; Single Lacoste; Polo Pique

Introduction

The art of knitting has been rapidly progressing day by day. Unlike woven fabrics, knitted fabrics are popular for their shape fitting properties; soft handle, bulkier nature and high extension at low tension. The application of knitting was popular by the term hose to produce a complete covering of the legs and since then the word hosiery is conveniently used for a series of articles on stockings, socks, knitted legs coverings, and even to general circular knitted goods [1]. Different types of knitted fabric may be produced by intermeshing different types of loops such as knit, tuck and miss loops. Along with knit loops, tuck loops are used to produce different types of commercial and popular knitted structures. The commercial design of knitted garments is a process that shares many important characteristics with other types of aesthetic design and engineering [2]. Yarn-dyed knit

fabric is one of exclusive fabric highly recommended by Buyer. In knitwear section yarn dyed fabric is very popular and expensive rather than regular solid fabric. For years, knitting has been considered more an art than a science. Many attempts have been made over the past century quantify the characteristics of knitted fabrics [3]. Knit fabrics provide comfortable wear to almost any style of garment. Most of the knitted fabric is used to produce baby wear without restricting movement.

While many variations of knit fabrics exist such that used for hosiery, only two types of knit fabric exist-weft and warp knits. From these two types of knit fabrics come various sub-types. The key to understanding a knitted structure lies within its basic element, the single knitted loop. The length of yarn knitted into a single loop will determine such overall fabric qualities as hand,

comfort, weight, extensibility, finished size, cover factor, and most importantly, fabric dimensional stability [4]. In this paper, we have tried to develop various feeder stripe single jersey structures on single jersey circular knitting machine and study on the effects of yarn counts, knit structures and stitch lengths on the depth of stripe.

Materials and Methods

Raw material

Methods

In this project work, three different counts of seven colors were used to produce samples. Yarns were collected from knitting laboratory. Count of each and every cone was tested by using wrap reel and balance. Obtained data were presented in (Tables 1-3) of annexure. Before knitting, machine servicing was done properly, all the setting points were checked, and yarn tension was ad-

justed. First, Single Jersey Plain fabrics were produced with three different counts at the VDQ 15.65 cm. Course length and stitch length were measured. The stitch length was found 2.80 mm. Data of course length and stitch length were presented in (Table 4) of annexure. Then cone arrangements and needle set out were changed for other samples. Single Jersey Plain, Single Lacoste, Polo Pique, and Double Lacoste structures were produced with 26 Ne yarn at stitch length 2.80 mm. Last of all, four different samples were knitted with 30 Ne yarn at four different stitch lengths such as 2.70 mm, 2.80 mm, 2.90 mm and 3.00 mm. Detail parameters were given in (Table 4). All the samples were then left lying on a smooth flat surface for 24 hours for dry relaxation. After relaxation, the depth of stripe and CPI for each sample were measured. Then hot wash was given to all samples by using AHIBA IR machine at 60° C for 10 min. Samples were then dried. After drying and conditioning, depth of stripe and CPI were measured.

Table 1: Raw Material of Samples.

Sl. No			
1	Yarn type	100% cotton combed dyed yarn	
2	Yarn count	26 Ne, 28 Ne, 30 Ne	
3	Package type	Cone	
4	Yarn color	26 Ne	Grey, Red, Black, Blue, White
		28 Ne	Grey, Red, Black, Blue, White
		30 Ne	Grey, Red, Black, Blue, White

Table 2: Specifications of Single Jersey Circular Knitting Machine.

Machine Type	Machine Type
Single Jersey Circular Knitting Machine	Single Jersey Circular Knitting Machine
Machine Gauge	Machine Gauge
24G	24G
Cylinder Diameter	Cylinder Diameter
10inches	10inches
No. of Feeders	No. of Feeders
30	30

Table 3: Instruments used for testing.

Sl. No	Name of Instruments	Origin
1	Wrap Reel	SDL International and Co. Ltd., England
2	HATRA Course Length Tester	SDL International and Co. Ltd., England
3	AHIBA IR. 11E048	Data color, U.S.A.

Table 4: Detail Parameters of Produced Samples.

Sample No.	Fabric structure	VDQ (cm)	Stitch length (mm)	Yarn count (Ne)	No. of active feeders
1	S/J plain (SJP)	15.65	2.8	30	26
2				28	
3				26	

4	SJP	15.65	2.8	26	24
5	Single Lacoste (S/L)				
6	(PPQ)				
7	(D/L)				
8	SJP	15.1	2.7	30	24
9		15.65	2.8		
10		16.21	2.9		
11		16.75	3		

Measurement of Course Length by HATRA Course Length Tester

The fabric was prepared in such a manner that the lengths of yarn forming complete knitted courses can be pulled out easily. All the samples for measuring stitch length (SL) were in tubular form. Samples were cut across the wales line by a scissor. The yarn clamp spring was set into HATRA tester at an approximate length, according to the indicator of the Board of HATRA. One end of the yarn of a course of a sample was attached to the clamp. Then according to the direction, the yarn was guided through pulleys by pulling out from the sample. At the end of the yarn, a weight was attached for giving appropriate tension in yarn. The course length (CL) of the samples were then measured from the scale of HATRA. Stitch length was calculated by using the following formula. The total no. of needles was 744.

$$\text{Stitch length} = \frac{\text{(Course length)}}{\text{(Total number of needles)}} \dots\dots\dots (1)$$

Measurement of Depth of Stripe

Eleven different types of samples were produced for the depth of stripe (DOS) measurement following testing standard: B. S. 5441; 1977. After conditioning for several hours, the samples were then laid on a large flat table for DOS measurement. Twenty reading were taken from each sample [5].

Measurement of Courses per Inch

Test samples were laid on a flat horizontal surface for removing wrinkles without stretching. Courses per inch (CPI) were measured using a counting glass following testing standard: B. S. 1051; 1981. For the measurement of CPI of Single Jersey Plain fabrics, the edge of the counting glass was positioned either parallel to or, perpendicular to the wale line. Courses were counted parallel to the wale line. For cross tuck constructions, courses per inch were

measured by counting the courses of an inch. Ten measurements for each sample were made.

Results and Discussion

In both relaxed states, it was evident that maximum depth of stripe (DOS) was found in Single Jersey Plain fabric knitted with 26 Ne and lowest DOS was observed in SJP knitted with 30 Ne. In dry relaxed state, variation in DOS for different yarn counts was observed but its values were very low (Figure 1). In the wet relaxed state, the effects of yarn count in DOS were clearer. Depth of stripe in dry relaxed for 30Ne, 28 Ne and 26 Ne were found 13.25 mm, 14.1 mm and 14.85 mm respectively but in wet relaxed state, the values were reduced due to shrinkage and they were 12.7 mm, 13.5 mm and 14.2 mm respectively (Figure 2). In dry relaxed state, highest stripe depth was found in Single Jersey Plain structures, and then, Single Lacoste, Polo Pique and Double Lacoste respectively. The same sequence was observed in wet relaxed state. The highest value of depth of stripe was observed in Single Jersey Plain fabric and its values were before wash 12.33 mm and after wash 11.30 mm. The lowest values of DOS were found in Double Lacoste structures and its value were before wash 7.85 mm and after wash 6.80 mm. Depth of stripe of other structures lie in between them. Depth of stripes of cross tuck structures such as Single Lacoste, Double Lacoste and Polo Pique were lower than Single Jersey Plain structures where all the stitches were knit stitch. It has been observed that the structures having only knit stitches gave the higher depth of stripe and the structures having tuck stitches gave the lower depth of stripe. The reasons behind this behavior are in knit stitch, the complete loop configurations are available but, in tuck stitches, the loop length is shortened, as Tuck loops reduce fabric length and length-wise elasticity, due to the higher yarn tension on the tuck and held loops causes them to rob yarn from adjacent knitted loops (Figure 3).




Figure 1: Effects of yarn counts on Depth of stripe.




Figure 2: Effects of Knit structures on Depth of Stripe (DOS).




Figure 3: Effects of Stitch lengths on Depth of stripe.

In dry relaxed state, it was observed that, depth of stripe (DOS) was increased with the increase of stitch length [6,7]. Highest depth was observed in sample 11 knitted with stitch length 3.00 mm, and lowest DOS was found in Sample 9 which was produced with stitch length 2.70 mm. Highest DOS was observed in the structure produced with stitch length 3.00 mm and its values were before wash 14.30 mm and after wash 13.95 mm. Lowest DOS was observed in the structure produced with stitch length 2.70 mm and its values were before wash 11.1 mm and after wash 10.9 mm. In dry relaxed state, there was no clear trend in DOS variations was observed but in wet relaxed state, trend in DOS variations was found. About 1.05 mm DOS were increased by increasing stitch length 0.10 mm. The reason behind this is increasing stitch length increases the loop length which in turn increases the depth of stripes [8,9].

Regression Analysis

Regression analysis is the most common statistical method for estimation of the relationship between a dependent variable

and one or more independent variables [10,11]. This method has the advantage of simplicity in describing the quantitative relationship between textile material properties. Therefore, the multiple regression analysis method was selected for establishing the relationships between fibre and yarn properties. At the beginning, the types of relationship between selected counts, stitch length (SL) as independent variables and depth of stripe before and after wash as dependent variables were checked individually by using curve estimation and correlation analysis. Statistical analysis indicated that there was a nearly linear relationship between them. Hence, the linear multiple regression analysis method was chosen for this study [12,13]. Statistical analyses were performed using SPSS 11.0.1 software. From the linear regression formula, it is evident that, the predicted values for DOS of counts 26, 28, 30 Ne not showed variation more than 5%. This also same for predicted values of stitch lengths which shows that the regression formula is accurate and can be used to predict the values during manufacturing knitted fabrics for estimation of DOS (Tables 5-7).

Table 5: Regression coefficients, t-values and significance level of variables of our linear regression model.

Model	Unstandardized Coefficients		Standardized Coefficients	t	Sig.
	B	Std. Error			
(Constant)	25.242	0.745	-0.892	33.886	0
Count, x1	-0.4	0.027			

BWDOS, y1= 25.242- (.400× x1)

Model	Unstandardized Coefficients		Standardized Coefficients	t	Sig.
	B	Std. Error	Beta		
(Constant)	25.483	0.355	-0.976	71.714	0
Count, x1	-0.431	0.013		-34.039	0
AWDOS, y2= 25.483- (.431× x1)					
Model	Unstandardized Coefficients		Standardized Coefficients	t	Sig.
	B	Std. Error	Beta		
(Constant)	-15.57	1.601	0.897	-9.722	0
SL, x2	10.075	0.561		17.943	0
BWDOS, y3= -15.57+ (10.075×x2)					
Model	Unstandardized Coefficients		Standardized Coefficients	t	Sig.
	B	Std. Error	Beta		
(Constant)	-16.71	0.903	0.965	-18.501	0
SL, x2	10.225	0.317		32.29	0
AWDOS, y4= -16.71+ (10.225×x2)					

Table 6: Analysis of variance (ANOVA) results, BWDOS= Before wash depth of stripe, AWDOS= After wash depth of stripe.

Quantity		Sum of Squares	df	Mean Square	F	P(Sig.)
BWDOS (For Count)	Regression	25.6	1	25.6	226.831	0
	Residual	6.546	58	0.11		
	Total	32.146	59			
AWDOS (For Count)	Regression	29.756	1	29.8	1158.621	0
	Residual	1.49	58	0.03		
	Total	31.246	59			
BWDOS (For Stitch length)	Regression	101.506	1	102	321.962	0
	Residual	24.591	78	0.32		
	Total	126.097	79			
AWDOS (For Stitch length)	Regression	104.551	1	105	1042.666	0
	Residual	7.821	78	0.1		
	Total	112.372	79			

Table 7: Showing predicted vs observed data.

Count(Ne)	Predicted BWDOS	Observed BWDOS	Predicted AWDOS	Observed AWDOS	Stitch length (mm)	Predicted BWDOS	Observed BWDOS	Predicted AWDOS	Observed AWDOS
26	14.842	14.85	14.277	14.2	2.7	11.6325	11.5	10.898	10.9
28	14.042	14.1	13.415	13.5	2.8	12.64	13	11.92	11.95
30	13.242	13.25	12.553	12.7	2.9	13.6475	13.85	12.943	12.95

Conclusion

In this paper an approach was taken to determine the stripe depth in different parameters. The linear regression analysis formula and its changes in different parameters can help to make an idea about the result while producing horizontal striped weft knitted fabric commercially. It was observed that values of depth of stripes were changed due to changing the yarn counts, knit

structures and stitch lengths. Highest depth of stripe was found in single jersey plain structures and lowest in Double Lacoste at constant yarn count and stitch length. Courser yarns give higher depth of stripe of a knit fabric [14,15]. It was also seen that depth of stripe increases by increasing stitch length. Considering all the variables, it can say that highest depth of stripe can be produced in Single Jersey Plain knitted with coarsest yarn at largest stitch length. In this work, the structures were produced on small

diameter machine [16]. Yet remarkable variation in depth of stripe was observed. If the structures are produced in a large diameter machine which is commercially available, the depth of stripe variation will be more. Knitters can take help in selecting proper yarn count and stitch length for a depth of stripe of a structure using linear regression formula.

References

1. Anbumani N (2007) Knitting Fundamentals, Machines, Structures and Developments. 1st eds. New Age International, India.
2. Eckert C, Stacey M (2003) Sources of Inspiration in Industrial Practice: The Case of Knitwear Design. *Journal of Design Research* 3: 1-30.
3. Hepworth B, Hepworth K, Leaf GAV (1970) The Plain Knitted Structure. *Tex Res J* 40(5): 863-870.
4. Munden DL (1959) The Geometry and Dimensional Properties of Plain-Knitted Structure. *J Textile Ins* 50(10): T448-T464.
5. Kadolph (2007) Quality Assurance for Textiles and Apparels. 2nd eds. Fairchild books, Uk.
6. Spencer DJ (2001) Knitting Technology. 3rd eds. England.
7. Thomas DGB (1971) An Introduction to Warp Knitting. 73.
8. http://www.ehow.com/about_5456692_knitwear.html.
9. Hasnat MA, Khan MS (2013) Formulating equations for calculating & controlling width, WPI, CPI & GSM of circular weft knitted fabric. *Bangladesh Textile Today* 6 (1).
10. Mogahzy YEI (2008) Engineering Textiles: Integrating the Design and Manufacture of Textile.
11. Lee J, Steen C (2014) Technical Sourcebook for Designers. United Kingdom: Bloomsbury Academic.
12. Poursartip A, Street K (1995) Proceedings of the Tenth International Conference on Composite Materials. Characterization and Ceramic Matrix Composites 4.
13. Murry LS (1997) ICCM-11 Proceedings: Textile Composites and Characterisation 5.
14. Ajgaonkar DB (1998) Knitting Technology. Universal Publishing Corporation, Mumbai.
15. Hannan MA, Islam MM, Kabir SMF, Abdullahil Kafi, Shamsuzzaman Sheikh (2014) Effect of Yarn Count & Stitch Length on Shrinkage, Gsm And Spirality Of Single Jersey Cotton Knit Fabric. *European Scientific Journal*. 10(36): 188-198.
16. Khalil E, Sarkar J, Solaiman M, Rahman MM (2014) Evaluation of Physico-Mechanical Properties of 1×1 Interlock Cotton Knitted Fabric Due to Variation of Loop Length. *International Journal for Research in Applied Science And Engineering Technology* 2(9): 193-197.



This work is licensed under Creative Commons Attribution 4.0 License
DOI: [10.19080/CTFTTE.2019.05.555657](https://doi.org/10.19080/CTFTTE.2019.05.555657)

Your next submission with Juniper Publishers will reach you the below assets

- Quality Editorial service
- Swift Peer Review
- Reprints availability
- E-prints Service
- Manuscript Podcast for convenient understanding
- Global attainment for your research
- Manuscript accessibility in different formats
(Pdf, E-pub, Full Text, Audio)
- Unceasing customer service

Track the below URL for one-step submission
<https://juniperpublishers.com/online-submission.php>